

















SUBLIMATION TRANSFER PAPER

FAST DRY HIGH SPEED			
<p>COMTransfer</p>  <p>SPFDRC6110P 100GSM</p>	<p>COMTransfer</p>  <p>SPFDRC6110B 94GSM</p>	<p>COMTransfer</p>  <p>SPFDRC6109 88GSM</p>	<p>COMTransfer</p>  <p>SPFDRC6109A 83GSM</p>
<p>COMTransfer</p>  <p>SPFDRC6108 78GSM</p>	<p>COMTransfer</p>  <p>SPFDRC6107D 66GSM</p>	<p>COMTransfer</p>  <p>SPFDRC6107 63GSM</p>	<p>COMTransfer</p>  <p>SPFDRC6105 48GSM</p>
<p>COMTransfer</p>  <p>SPFDRC6104 44GSM</p>	<p>COMTransfer</p>  <p>SPFDRC5104 35GSM</p>	<p>COMTransfer</p>  <p>SPFDRC6110AC 100GSM</p>	<p>COMTransfer</p>  <p>SPFLRC6310 100GSM</p>
STICKY TACKY		INSTANT DRY	
<p>COMTransfer</p>  <p>SPSTRC6210 100GSM</p>	<p>COMTransfer</p>  <p>SPFDRC6610 100GSM</p>	<p>COMTransfer</p>  <p>SPIDRC8410 100GSM</p>	<p>COMTransfer</p>  <p>SPIDRC8410AC 100GSM</p>



Add: Room 912, No.3 Building, Shangdong Business Center, Haizhou District,
Haining, Zhejiang, China
Tel: +86-573-80776996 Fax: +86-573-80776998
Mob/Skype/Wechat/WhatsApp: +86-15858322153
<mailto:contact@hncomax.com> <https://www.hncomax.com>



SUBLIMATION TRANSFER PAPER

ITEM CODE	FEATURE	WEIGHT	AVAILABLE SIZE
SPFDRC6110P	Fast Dry	100gsm	
SPFDRC6110B	Fast Dry	94gsm	
SPFDRC6109	Fast Dry	88gsm	
SPFDRC6109A	Fast Dry	83gsm	
SPFDRC6108	Fast Dry	78gsm	
SPFDRC6107D	Fast Dry	66gsm	Mini Roll/Jumbo Roll
SPFDRC6107	Fast Dry	63gsm	
SPFDRC6105	Fast Dry	48gsm	
SPFDRC6104	Fast Dry	44gsm	
SPFDRC5104	Fast Dry	35gsm	
SPSTRC6210	Sticky Tacky	100gsm	
SPFLRC6310	Fast Dry Low Temperature	100gsm	
SPFSRC6610	Fast Dry Sticky Tacky	100gsm	
SPFDRC6110	Fast Dry	98gsm	Mini Roll/Jumbo
SPIDRC8410	Instant Dry	100gsm	Roll/A3/A4



Add: Room 912, No.3 Building, Shangdong Business Center, Haizhou District,
Haining, Zhejiang, China
Tel: +86-573-80776996 Fax: +86-573-80776998
Mob/Skype/Wechat/WhatsApp: +86-15858322153
<mailto:contact@hncomax.com> <https://www.hncomax.com>



STORAGE OF SUBLIMATION TRANSFER PAPER

Sublimation transfer paper should be stored in a cool and dry place and avoid direct sunlight. It is better to store the paper under constant temperature and humidity in air-conditioned rooms. The ideal storage condition is a relative humidity of 40-70%RH under 10-30°C.

Sticky transfer paper has strong moisture absorption capacity, and its viscosity will change in different temperature and humidity environments. Please be sure to store it in an environment where the relative humidity is less than 70% RH and tie the plastic bag in a cool place away from the light.

PRINTING OF TRANSFER PAPER

The printing environment humidity is preferably controlled at around 45-65% RH, as if the environment is too dry, the transfer paper is curled. Then when printing in large amounts of ink, the transfer paper may arch so it may stretch out and collide into the printing heads and cause malfunctioning. If the environment is too humid, then it may cause the reduction of drying rate of transfer paper and the irregularity of transfer paper's stretch at both ends of the paper. The printing room is recommended to install air-conditioning and dehumidifier to ensure that the printing environment is stable and appropriate.

STORAGE OF PRINTED-PAPER

Keep the paper roll in a loose plastic bag and keep it upright, do not seal the plastic bag so that the moisture from the transfer paper can be evaporated into the air. It is better to store the printed transfer paper in an environment with a humidity of 45-65% RH and a temperature of 15-30°C.



Add: Room 912, No.3 Building, Shangdong Business Center, Haizhou District,
Haining, Zhejiang, China
Tel: +86-573-80776996 Fax: +86-573-80776998
Mob/Skype/Wechat/WhatsApp: +86-15858322153
<mailto:contact@hncomax.com> <https://www.hncomax.com>

